

## MOTOR BEARING GREASE RELUBRICATION INTERVALS (IN MONTHS)

RPM	HP Range	8 hrs/day Clean	8 hrs/day Dirty	24 hrs/day Clean	24 hrs/day Dirty
3600	0.5 - 7.5	12	6	6	3
	10 - 40	9	4	4	2
	50 - 150	9	4	4	2
1800	0.5 - 7.5	36	18	18	9
	10 - 40	24	9	12	4
	50 - 150	18	9	9	4
1200	0.5 - 7.5	48	24	24	12
	10 - 40	36	12	18	6
	50 - 150	12	12	12	6

## NLGI GREASE COMPATIBILITY CHART

	Aluminum Complex	Barium	Calcium	Calcium 12-hydroxy	Calcium Complex	Clay	Lithium	Lithium 12-hydroxy	Lithium Complex	Polyurea
Aluminum Complex	X	I	I	C	I	I	I	I	C	I
Barium	I	X	I	C	I	I	I	I	I	I
Calcium	I	I	X	C	I	C	C	B	C	I
Calcium 12-hydroxy	C	C	C	X	B	C	C	C	C	I
Calcium Complex	I	I	I	B	X	I	I	I	C	C
Clay	I	I	C	C	I	X	I	I	I	I
Lithium	I	I	C	C	I	I	X	C	C	I
Lithium 12-hydroxy	I	I	B	C	I	I	C	X	C	I
Lithium Complex	C	I	C	C	C	I	C	C	X	I
Polyurea	I	I	I	I	C	I	I	I	I	X

**B = Borderline Compatibility; C = Compatible; I = Incompatible.**